

# Cold Spray Coatings for Prevention and Mitigation of Stress Corrosion Cracking

Arash Parsi <sup>1</sup>, Jack Lareau <sup>1</sup>

Brian Gabriel <sup>2</sup>, Victor Champagne <sup>2</sup>

<sup>1</sup> Westinghouse Electric Co LLC, 1340 Beulah Road, Pittsburgh, PA

<sup>2</sup> Army Research Laboratory, Aberdeen Proving Grounds, MD



# Addressing Nuclear Concerns

---

- Austenitic Ni and Fe alloys comprise the bulk of wetted surfaces in nuclear power plants
- These alloys are susceptible to stress corrosion cracking (SCC) especially after extended service life
- Repair and mitigation of components in the field is difficult and costly
- A cost-effective field-deployable methodology to protect that affected surfaces is desired
- Cold Spray offers tremendous advantages in preventing SCC from initiating and repair of existing affected zones

# Cold Spray Advantages for Nuclear Applications

---

- No heat affected zone
- Wrought, not cast, structure
- Compressive surface layer
- Minimal surface preparation required
- Machines like normal metal
- High adhesion (>10 ksi)
- Can be easily applied using robotics
- Surface is inspectable with PT and UT\*

\*without an inspectable coating, all other attributes are academic

# Cold Spray Nickel


---

- Nickel is much more resistant to SCC at primary water conditions than austenitic alloys
- Nickel comprises ~70% of wetted non-fuel surface area in the plant
- It is isotropic, homogeneous, and doesn't have any secondary phases
- Nickel is available commercially as a high purity cold-sprayable powder

# The Ni-Alloy 600 Interface

---

The coating is as good as the interface



Note the clean, well-bonded interface and pore-free coating

# Tests Completed

---

To determine the efficacy of the coating for primary water applications, the test program encompassed the following:

- Coating morphology (cross-section, roughness)
- Mechanical properties (fatigue, ductility, adhesion, etc.)
- Inspectability (UT and PT)
- Ability to protect against SCC (halide/sulfate doped steam)
- Coating complex surfaces

**Testing conducted over 18 months on  
200+ various specimens**



# Mechanical Testing

---

- Ductility

- Ductility of as-deposited Ni >2.25% strain

- Hardness

- Vickers performed on polished x-section of coating, showed

- Adhesion

- Consistent consistency in hardness (~250 VHN)
  - Specimens bent 180° over a mandrel three times and flattened
  - Coating cracked but did not spall or disbond

- Cyclic Fatigue

- 4-point fatigue, 50000 cycles,  $22.5 \pm 21$  ksi tensile stress load

- Thermal Cycling

- UT, PT and SEM showed no coating cracking or disbonding
  - Heated to 400 °C and plunged in water for 100 cycles


- Impact Testing

- UT, PT and SEM showed no coating cracking or disbonding
  - Coating struck with a round-nosed weight with 10J energy and showed no cracking or spalling

# Coating Ductility



25 °C




270 °C

- Room temperature cracking observed at ~2.25-2.5% strain
- At 270 °C, cracking is observed at 8-9% strain
- At 350 °C, no cracking observed up to 16%



# Cross-Section Vickers Hardness





CS Ni Coating:  $264 \pm 9$  VHN

Alloy 600 Substrate:  $175 \pm 7$  VHN


# Adhesion Strength by Bending

- Bend bars bent 180° around a mandrel and flattened 3 times
- Coating cracks but remains adhered over the entire surface
- No delamination from the Alloy 600 substrate






# UT Inspection




Inspection  
Frequency – 25 MHz



# Fatigue


- 4-point fatigue testing to determine coating behavior under cyclic loads
- 50,000 cycles, mean tensile stress of 22.5 ksi (50% of yield) and stress amplitude of  $\pm 21.7$  ksi





# Thermal Cycling



- No change in UT signal for any sample, indicating a tightly adherent coating which is not susceptible to thermal shock



**After 500 cycles**

# Impact Testing


- Surface structure analyzed by SEM/EDS to determine if 10 J of presence (Causes) of cracks exposing the substrate



# Doped Steam SCC Testing

---

- Testing performed on strain-hardened 1/8" thick and 1/4" thick Alloy-182 clad bend bars
- Fully and partially coated specimens tested
- Specimens stressed to 70, 75 and 80 ksi tensile
- Corrosion testing carried out at 750° F, 5-13 psia H<sub>2</sub>, 80 ppm of F<sup>-</sup>, Cl<sup>-</sup> and SO<sub>4</sub><sup>2-</sup>





# Doped Steam SCC Testing

---

- 1/8" Alloy 600 bend bars: control specimens cracked within 200 hours, coated specimens did not crack (1000 hrs total testing)
- 1/4" Alloy 182-clad bend bars: control specimens cracked within 200 hours, coated specimens did not crack (800 hrs total testing)
- Doped steam testing accelerates onset of SCC by >300 x, suggesting that cold spray Ni can protect Alloy 600 > 34 yrs\*


(\*) *Materials Reliability Program: An Assessment of the Control Rod Drive Mechanism (CRDM) Alloy 600 Reactor Vessel Head Penetration PWSCC Remedial Technique (MRP-61)*, EPRI, Palo Alto, CA: 2003.1008901.



# Doped Steam SCC Testing

After 200 hrs

After 1000 hrs



# Stainless Steel Pipe Coating

---

- 360° band, 3" wide, shown as coated with no post surface preparation
- Coated with oxide removed ("Blasted") and as received ("Oxidized")
- "Pipe over a pipe" increases burst strength



# Carbon Steel Plate with Excavation

---

- 30% of wall machined away to simulate corrosion, oxide removed
- UT show strong bond
- Surface finished with hand held flapper wheel





# Summary

---

- Successful application of pure Ni coating using Cold Spray on Alloy 600 for SCC mitigation
- Mechanical tests show the recipes to be sufficiently ductile for intended application and resilient (fatigue, thermal cycling, impact, etc.)
- Doped steam tests show the Ni coatings protect substrate against SCC for an extended period of time
- Cold Spray shows great promise in corrosion mitigation for very demanding applications